



## Net banner 270 gr/m<sup>2</sup>

### TECHNICAL DATA

ITEM	DATA	UNIT	TEST METHOD
Fabric	High tenacity yarns 100% PES (250D*250D)		DIN EN ISO 2060
Construction	Weaving 12*12	inch	DIN 60001
Total weight	270	g/sq.m	DIN53352 BS3424 method5A
Weight of fabric	100	g/sq.m	DIN53352 BS3424 method5B
Weight of PVC	170	g/sq.m	DIN53352 BS3424 method5B
Tensile strength	Warp: 1250 Weft: 1100	N/5cm	DIN53354 BS3424 method6A
Tearing strength	Warp: 235 Weft: 220	N	DIN53356 BS3424 method 7A
Air permeability	33%		
Suitable temperature	-20 to +70	C	DIN 53372 BS3424 method10
Flame retardancy	B1		

#### Disclaimer

All Carl Jensen's products are subject to manufacturing controls in order to guarantee the good quality of the products. The statements, technical information, data, values and recommendations regarding Carl Jensen's products are based on research and tests we believe to be reliable, but do not constitute a guarantee or warranty of whatsoever nature.

Considering the multiple uses of Carl Jensen's products, the user is recommended to test the products prior to their use, so to determine and ascertain the suitability and performance of the product for its intended application and purpose.

The methods of conversion and application of Carl Jensen's self-adhesive materials are multiple and it is therefore essential that the users are aware of the particular method to be used, prior to commencing the production.

Printing: Testing for compatibility between product, printers and inks is always highly recommended before printing the product.



Application Systems and Conditions: it is recommended that the performance of the product be always tested in the actual applications conditions as substrate state (rough, smooth, flat or irregular shapes, moderate curves, with or without rivets); applicator technology (hand application or fully automated lines); specific stress on Carl Jensen material once applied (high and/or low temperature, mechanical stress, exposure to challenging environment conditions), et cetera.

As Carl Jensen's products are used in conditions beyond its control, such as those listed above as example, Carl Jensen does not assume any liability for inappropriate use of the products.

Carl Jensen reserves the right to modify at any time and without the need of a prior notice, at its sole and exclusive discretion, the products, their features and technical specifications.

All Carl Jensen's products are sold subject to Carl Jensen's general terms and conditions of sale listed in the following Carl Jensen's web page: [www.carl-jensen.com](http://www.carl-jensen.com)